

ACCIAI PER LAVORAZIONI A FREDDO

Segmenti di applicazione

Lavorazione a freddo

Granulometria disponibile

Prodotti lunghi

Descrizione del prodotto

BÖHLER K346 belongs to the group of conventionally produced 8% chromium steels. Its alloy composition features a high content of molybdenum, tungsten and vanadium, which makes BÖHLER K346 more wear resistant and tougher than conventional 12% chromium steels (1.2080, 1.2379). BÖHLER K346 is used in situations where materials like 1.2379 are insufficient in terms of toughness and where high requirements for abrasive wear resistance are set. This combination of high wear resistance and toughness offers advantages for industrial knives subject to high stress in the recycling industry. This grade is also used for stamping and cutting tools.

Percorso di fusione

Forno ad arco/EAF

Proprietà

- > Durezza e duttilità : buono
- > Resistenza all'usura : alto
- > Resistenza alla compressione : alto
- > Stabilità dimensionale : alto

Applicazioni

- > Coltelli da macchina (per i produttori)
- > Componenti per l'industria del riciclaggio
- > Componenti per costruzioni sotterranee (perforazioni, pozzi, ecc.)
- > Rullaggio del filo

Analisi chimica

C	Si	Mn	Cr	Mo	V
1,13	1,20	0,35	7,80	1,60	2,40

Proprietà del materiale

	Resistenza alla compressione	Stabilità dimensionale durante il trattamento termico	Tenacità	Abrasivo resistente all'usura	Adesivo resistente all'usura
BÖHLER K346	★★★	★★★	★★★	★★★★★	★★
BÖHLER K100	★★	★★	★	★★★★	★★
BÖHLER K105	★★	★★	★	★★	★★
BÖHLER K110	★★	★★★	★	★★★★	★★
BÖHLER K190 MICROCLEAN	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★
BÖHLER K294 MICROCLEAN	★★★★★	★★★★★	★★★	★★★★★	★★★★★
BÖHLER K340 ECOSTAR	★★★	★★★	★★	★★	★★
BÖHLER K340 ISODUR	★★★	★★★★★	★★★	★★★	★★★★★
BÖHLER K353	★★	★★★	★★	★★	★★
BÖHLER K360 ISODUR	★★★	★★★★★	★★★	★★★★★	★★★★★
BÖHLER K390 MICROCLEAN	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★
BÖHLER K490 MICROCLEAN	★★★★★	★★★★★	★★★★★	★★★★★	★★★★★
BÖHLER K497 MICROCLEAN	★★★★★	★★★★★	★★★	★★★★★	★★★★★
BÖHLER K888 MATRIX	★★★★★	★★★★★	★★★★★	★★	★★
BÖHLER K890 MICROCLEAN	★★★★★	★★★★★	★★★★★	★★★	★★★

Condizioni di consegna

Ricotto

Durezza (HB)	max. 250
--------------	----------

Trattamento termico

Ricottura

Temperatura	840 a 870 °C	Slow controlled cooling in furnace at a rate of 10 to 20 °C/hr (18 to 36 °F/hr) down to approximately 600 °C (1112 °F) Further cooling in air.
-------------	--------------	---


Alleviare lo stress

Temperatura	650 °C	After through heating, hold in neutral atmosphere for 1-2 hours. Slow cooling in furnace Intended to relieve stresses caused by extensive machining or in complex shapes.
-------------	--------	---

Tempra e rinvenimento

Temperatura	1.050 a 1.090 °C	Quenching: Oil, gas, air. Holding time after temperature equalization: 15 to 30 minutes. After hardening, tempering to the desired working hardness according to the tempering chart.
-------------	------------------	---

Tempering Chart



Specimen profile: 7x10 mm (0,28x0,39 inch)

Slow heating to tempering temperature immediately after hardening.

Time in furnace 1 hour for each 20 mm (0,787 inch) of workpiece thickness but at least 2 hours.


Please refer to the tempering chart for guide values for the achievable hardness after tempering.

It is recommended to temper at least three times at 540 °C (1004 °F) for 2 hours.

Cooling in air to room temperature after each tempering step is recommended.

Tempering for stress relieving 30 to 50 °C (86 to 122 °F) below the highest tempering temperature.

Continuous cooling CCT curves



Austenitising temperature: 1070 °C (1958 °F)
Holding time: 30 minutes

10....90 phase percentages
Cooling parameter λ ... duration of cooling from 800 to 500 °C (1472 to 932 °F) in s x 10⁻²

A... Austenite
K... Carbide
P... Pearlite
Zw... Bainite
Ms... Martensite starting temperature

Probe	(DIL805) Vers.Nr.	λ	HV _{0.05}	RA%	Probe	(DIL805) Vers.Nr.	λ	HV _{0.05}	RA%
a	2151	0.1	812	14	g	2154	30	610	7
b	2153	0.5	810	13	h	2180	65	370	1
e	2148	1.1	810	12	j	2183	110	260	<1
d	2156	3	790	16					
e	2182	8	760	14					
f	2158	23	680	13					

Proprietà fisiche

Temperatura (°C)	20
Densità (kg/dm ³)	7,64
Conducibilità termica (W/(m.K))	22
Capacità termica specifica (kJ/kg K)	0,47
Resistenza elettrica specifica (Ohm.mm ² /m)	0,6
Modulo di elasticità (10 ³ N/mm ²)	220

Espansioni termiche

Temperatura (°C)	100	200	300	400	500	600	700
Espansione termica (10 ⁻⁶ m/(m.K))	11	11,5	12	12,4	12,7	13	13,2

Le specifiche contenute in questo opuscolo non sono vincolanti e non devono essere considerate come promesse, ma solo come informazioni generali. Queste specifiche sono vincolanti solo se vengono espressamente poste come condizione in un contratto stipulato con noi. I dati misurati sono valori di laboratorio e possono discostarsi dalle analisi pratiche. Nella fabbricazione dei nostri prodotti non vengono utilizzate sostanze nocive per la salute o per lo strato di ozono.