

# CORROSION RESISTANT STEELS - MARTENSITIC PRECIPITATION HARDENING (PH) STEELS

Ap	pli	cat	ion	Se	gm	en	ts

Aerospace Automotive

## **Available Product Variants**

Semi-Finished Products / Billet Long Products\* Plates

## **Product Description**

BÖHLER N700 is a high-quality corrosion-resistant steel in aerospace quality, in the form of bars, wire and forgings with a diameter/thickness of up to 203 mm in the solution-annealed condition, as well as starting material of any size for forging purposes It is a martensitic, precipitation-hardenable chromium-nickel-copper steel with high strength and toughness. Further increases in strength can

be achieved by cold forming and subsequent precipitation hardening. These products are typically used for parts requiring corrosion resistance and high strength up to 316°C. However, their use is not limited to such applications. However, use is not limited to such applications.

Certain processing methods and operating conditions can cause these products to become susceptible to stress corrosion cracking.

For applications such as bolting where stress corrosion cracking is possible, the product should be aged for a minimum of 4 hours at the highest temperature compatible with the strength requirements, but in no case lower than 552°C.

## **Process Melting**

Airmelted + VAR

## **Applications**

- > Aerospace Automotive
- > Other Aerospace Components
- Motorsport industry
- > Structural parts (Aerospace)
- > Other Automotive Components (Turbochargers, Piston Rings, Sensors, etc.)

# Technical data

Material designation				
17-4 PH	Market grade			
1.4548	SEL			
X5CrNiCu17-4 EZ6CNU17.04	EN			
S17400	UNS			
630	AISI			

Standards		
	A564	ASTM
	5643 5622	AMS



<sup>\*</sup> Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).



# CORROSION RESISTANT STEELS - MARTENSITIC PRECIPITATION HARDENING (PH ) STEELS

# Chemical composition (wt. %)

С	Si	Mn	Р	S	Cr	Мо	Ni	Cu	Nb
max. 0.07	max. 1.00	max. 1.00	max. 0.025	max. 0.015	15.00 to 17.50	max. 0.50	3.00 to 5.00	3.00 to 5.00	5xC to 0.45

Related to AMS 5622 type 1

# **Delivery condition**

Solution annealed						
Hardness (HB)	max. 363   bars, hot or cold finished, forgings					
Tensile Strength (MPa)	max. 1,207   for wire products					

### Round Bars and Wire Rod (if any)

D	Diameter		MOQ ex mill	Le	eng	gth	Tolerance		
	mm	ı	kg	m					
5.01	-	12.49	1,100	3.00 - 4.00		4.00	IT h/k 11		
12.50	-	55.00	1,200	3.00 -		4.00	IT h/k 11		
55.01	-	120.00	2,297	3.00 -		4.00	IT h/k 11		
120.01	-	140.00	2,300	3.00	-	5.00	IT h/k 14		
FORGED									
140.01	-	203.20	2,350	2.00 - 5.00			IT h/k 14		

### Flat Bars

١	Width		Thickness		ess	MOQ ex mill	Lengt		h	Tolerance
	mm		mm		1	kg	m			
	ROLLED									
15.00	-	121.00	8.00	-	86.00	1,300	3.00	-	4.00	LN 1017
120.00	-	150.00	25.00	-	85.00	2,550	3.00	-	4.00	LN 1017
150.00	-	275.00	20.00	-	100.00	2,550	3.00	-	4.00	LN 1017
275.00	-	330.00	25.00	-	80.00	2,550	3.00	-	4.00	LN 1017

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

## voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25 8605 Kapfenberg, AT T. +43/50304/20-0

E. info@bohler-edelstahl.at

https://www.voestalpine.com/bohler-edelstahl/de/

