

ACCIAI DA UTENSILE PER LAVORAZIONE A CALDO

Segmenti di applicazione

Lavoro a caldo

Automotive

Granulometria disponibile

Prodotti lunghi

Descrizione del prodotto

BÖHLER W460 VMR is a double vacuum arc remelted (VAR) material that has been specially adapted for use in the motorsport sector. The steel purity achieved by this special manufacturing technology, combined with the high strength, ensures that a very high fatigue strength can be guaranteed. The high purity also results in very good polishability, which makes the steel a good choice as a tool material for minting coins.

Percorso di fusione

Airmelted + VAR + VAR

Applicazioni

> Industria del motorsport > Coniatura > Componenti generali per l'ingegneria meccanica

Dati tecnici

Corrispondenze

BÖHLER patent	Market grade
---------------	--------------

Analisi chimica

C	Si	Mn	Cr	Mo	V
0,50	0,20	0,45	4,60	3,00	0,75

Condizioni di consegna

Ricotto

Durezza (HB)	max. 205
--------------	----------

Trattamento termico

Ricottura

Temperatura	750 a 800 °C	Holding time 6 to 8 hours. Slow, controlled furnace cooling at 10 to 20°C/h (50 to 68 °F/hr) to approx. 600°C (1112°F), further cooling in air.
-------------	--------------	---

Alleviare lo stress

Temperatura	650 a 700 °C	For stress relief after extensive machining or for complicated tools. Holding time depending on tool size after complete heating 2 - 6 hours in neutral atmosphere. Slow furnace cooling.
-------------	--------------	---

Tempra e rinvenimento

Temperatura	1.050 a 1.070 °C	Holding time after temperature equalization: 15 to 30 minutes; Quenching: Oil, salt bath (500 - 550°C [932-1022°F]), air, vacuum; After hardening, tempering to the desired working hardness (see tempering chart).
-------------	------------------	---

Espansioni termiche

Temperatura (°C)	100	200	300	400	500	600	700
Espansione termica (10 ⁻⁶ m/(m.K))	11,1	11,5	11,9	12,3	12,8	13,2	13,6

Le specifiche contenute in questo opuscolo non sono vincolanti e non devono essere considerate come promesse, ma solo come informazioni generali. Queste specifiche sono vincolanti solo se vengono espressamente poste come condizione in un contratto stipulato con noi. I dati misurati sono valori di laboratorio e possono discostarsi dalle analisi pratiche. Nella fabbricazione dei nostri prodotti non vengono utilizzate sostanze nocive per la salute o per lo strato di ozono.