

ACCIAI DA UTENSILI PER LAVORAZIONE A FREDDO

Granulometria disponibile

Prodotti lunghi*

Lamiere

*) Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

Descrizione del prodotto

BÖHLER K320 corresponds to the material 1.2355 (50CrMoV13 -15, S7). According to the AISI classification system, this tool steel belongs to the group of impact-resistant tool steels (S types). This popular tool steel offers high toughness and good machinability with moderate wear resistance. BÖHLER K320 is used in cold and hot work applications as well as in plastic mold making. This tool steel is used for a wide range of tools where impact strength, good machinability and simple heat treatment are important.

Percorso di fusione

Airmelted

Proprietà

- > Durezza e duttilità : buono
- > Resistenza all'usura : buono
- > Resistenza alla compressione : buono
- > Stabilità dimensionale : buono

Applicazioni

- > Lame automatiche (per produttori)
- > Laminazione a freddo
- > Stampaggio a freddo
- > Tranciatura / Tranciatura fine / Stampaggio
- > Pressatura delle polveri

Dati tecnici

Corrispondenze	
~1.2357	SEL
~50CrMoV13-14	EN
S7	AISI

Analisi chimica

C	Si	Mn	Cr	Mo	V
0,53	0,30	0,60	3,25	1,45	0,25

Proprietà del materiale

	Resistenza alla compressione	Stabilità dimensionale durante il trattamento termico	Tenacità	Abrasivo resistente all'usura
BÖHLER K320	★★★	★★★	★★★	★★★
BÖHLER K305	★★★★★	★★★	★★	★★★★★
BÖHLER K306	★★★★★	★★★	★★★★★	★★★
BÖHLER K313	★★★★★	★★★	★★★	★★★
BÖHLER K329	★★★	★★★	★★★★★	★★★★★
BÖHLER K600	★	★★★	★★★★★	★
BÖHLER K601	★	★★★	★★★★★	★★
BÖHLER K605	★★	★★★	★★★★★	★

Condizioni di consegna

Ricotto

Durezza (HB)	max. 225
--------------	----------

Trattamento termico

Annealing

Temperatura	820 a 850 °C	Slow controlled cooling in furnace at a rate of 10 to 20°C/hr down to approx. 600°C, further cooling in air.
-------------	--------------	--

Alleviare lo stress

Temperatura	600 a 650 °C	Slow controlled cooling in furnace at a rate of 10 to 20°C/hr down to approx. 600°C, further cooling in air. After through heating, hold in neutral atmosphere for 1 to 2 hours.
-------------	--------------	--

Tempra e rinvenimento

Temperatura	930 a 950 °C	Air, oil Holding time after temperature equalization: 15 to 30 minutes.
-------------	--------------	---

Long Products: For additional specifications and technical requirements, please contact our regional voestalpine BÖHLER sales companies.

Sheet & Plates: Product Variant may differ in terms of melting process, technical data, delivery, and surface condition as well as available product dimensions. Please contact voestalpine BÖHLER Bleche GmbH & Co KG.

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.