

ACCIAI RAPIDI

Granulometria disponibile

Prodotti lunghi*

Lamiere

*) Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

Descrizione del prodotto

Acciaio rapido ottenuto mediante procedimento di metallurgia delle polveri con buona durezza a caldo, resistenza alla compressione e all'usura. La tecnologia della metallurgia delle polveri permette una buona tenacità e un'eccezionale lavorabilità e rettificabilità.

Percorso di fusione

Powder metallurgy

Proprietà

- > Durezza e duttilità : alto
- > Resistenza all'usura : buono
- > Resistenza alla compressione : buono
- > Stabilità dei bordi : buono
- > Macinabilità : alto
- > Durezza a caldo (durezza rossa) : buono

Applicazioni

- > Corsa
- > Pressatura delle polveri
- > Utensili speciali per lavorazioni con asportazione di truciolo
- > Brocche e alesatori
- > Laminazione a freddo
- > Parti soggette a usura
- > Coniatura / Formatura a freddo
- > Lame industriali / Cesoie

Dati tecnici

Corrispondenze		Standard	
1.3345	SEL	4957	EN ISO
HS6-5-3C	EN		

Analisi chimica

C	Cr	Mo	V	W
1,29	4,2	5	3	6,3

Proprietà del materiale

	Resistenza alla compressione	Macinabilità	Durezza a caldo	Tenacità	Resistenza all'usura	Resistenza al taglio
BÖHLER S290 MICROCLEAN	★★★★★	★	★★★★	★★	★★★★★	★★★★
BÖHLER S390 MICROCLEAN	★★★★	★★★	★★★★	★★★★	★★★★	★★★★
BÖHLER S393 MICROCLEAN	★★★★	★★★	★★★★	★★★★	★★★★	★★★★
BÖHLER S590 MICROCLEAN	★★★★	★★★	★★★★	★★★	★★★	★★★
BÖHLER S690 MICROCLEAN	★★★	★★★	★★	★★★★★	★★★	★★
BÖHLER S793 MICROCLEAN	★★★	★★★	★★★★	★★★	★★★	★★★

Condizioni di consegna

Ricotto

Durezza (HB)	max. 280 drawn max. 300 HB
Resistenza allo snervamento (N/mm ²)	max. 1.020

Trattamento termico

Annealing

Temperatura	870 a 900 °C	870 to 900°C (1598 to 1652°F) The steel needs to be protected against decarburization. Through heating of the material is followed by controlled, slow furnace cooling at a maximum cooling rate of 10°C (50°F) per hour, down to approx. 700°C (1292°F). Final cooling in air.
-------------	--------------	--


Alleviare lo stress

Temperatura	600 a 650 °C	Slow cooling furnace. To relieve stresses set up by extensive machining or in tools of intricate shape. After through heating, hold in neutral atmosphere for 1 to 2 hours.
-------------	--------------	---

Tempra e rinvenimento

Temperatura	1.050 a 1.200 °C	Salt bath, vacuum Preheating: 1st stage ~ 500 °C, 2nd stage ~ 850 °C, 3rd stage ~1050 °C (for higher austenitising temperature) Austenitising: for cutting applications at higher austenitising temperatures (> 1130 °C), holding time after complete heating 80 seconds, maximum 150 seconds, to avoid material damage due to overtime. Austenitising: for cold work applications at lower austenitising temperatures (< 1100°C). Holding time after complete heating 15 to 30 min Quenching: oil, warm bath (500 - 550 °C), gas.
Temperatura	560 a 580 °C	Slow heating to tempering temperature immediately after austenitising. Dwell time in the furnace 1 hour per 20 mm material thickness (at least 1 hour) Slow cooling to room temperature between each tempering step 3 tempering cycles recommended Hardness see tempering chart


Continuous cooling CCT curves



Austenitising temperature: 1180°C (2156°F)
Holding time: 180 seconds

- A....Austenite
- B....Bainite
- K....Carbide
- P....Pearlite
- M....Martensite
- RA...Retained Austenite


Quantitative phase diagram



- A....Austenite
- B....Bainite
- K....Carbide
- P....Pearlite
- M....Martensite
- RA...Retained Austenite

- 1....Edge or Face
- 2....Core
- 3....Jominy test: distance from quenched end

Tempering Chart



Holding time 3 x 2 hours
Specimen size: square 25 mm

Proprietà fisiche

Temperatura (°C)	20
Densità (kg/dm ³)	8
Conducibilità termica (W/(m.K))	24
Capacità termica specifica (kJ/kg K)	0,42
Resistenza elettrica specifica (Ohm.mm ² /m)	0,54
Modulo di elasticità (10 ³ N/mm ²)	230

Espansioni termiche

Temperatura (°C)	100	200	300	400	500	600	700
Espansione termica (10 ⁻⁶ m/(m.K))	11,5	11,7	12,2	12,4	12,7	13	12,9

Long Products: For additional specifications and technical requirements, please contact our regional voestalpine BÖHLER sales companies.

Sheet & Plates: Product Variant may differ in terms of melting process, technical data, delivery, and surface condition as well as available product dimensions. Please contact voestalpine BÖHLER Bleche GmbH & Co KG.

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG
 Mariazeller Straße 25
 8605 Kapfenberg, AT
 T. +43/50304/20-0
 E. info@boehler-edelstahl.at
<https://www.voestalpine.com/boehler-edelstahl/de/>

ONE STEP AHEAD.